

LEXAN™ 9034 Sheet

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ 9034 uncoated polycarbonate sheet is the standard grade of LEXAN sheet for transparent protective glazing. High-impact LEXAN 9034 sheet may be an excellent candidate for primary glazing, or on either side of existing glazing for economical protection against breakage or intrusion. A better insulator than glass, LEXAN 9034 sheet may contribute to lower energy costs.

TYPICAL PROPERTY VALUES ◆

Property	Test Method	Units	Value
Physical			
Specific Gravity	ASTM D792	—	1.20
Refractive Index @ 77°F	ASTM D542A	—	1.586
Light Transmission (Average), 1/8" disk	ASTM D1003	%	88
Rockwell Hardness	ASTM D785	—	M70
Abrasion Resistance, Taber Abrader, CS-17 wheel	ASTM D1044	mg/1,000 cycles	10
Water Absorption, Equilibrium, 24 hrs	ASTM D570	%	0.15
@ 73°F			0.35
@ 212°F			0.58
Mechanical			
Tensile Strength @ Yield	ASTM D638	psi	9,000
@ Ultimate			9,500
Tensile Modulus	ASTM D638	psi	345,000
Flexural Strength	ASTM D790	psi	13,500
Flexural Modulus	ASTM D790	psi	345,000
Flexural Endurance @ 1,800 cycles/min,			
73°F, 50% RH	ASTM D671	psi	1,000
Compressive Strength	ASTM D695	psi	12,500
Compressive Modulus	ASTM D695	psi	345,000
Elongation	ASTM D638	%	110
Poisson's Ratio	—	—	0.37
Izod Impact Strength Notched @ 1/8"	ASTM D256A	ft-lbs/in	12–16
Unnotched @ 1/8"			60 (no failure)
Tensile Impact Strength, S-Type Specimen	ASTM 1822	ft-lbs/in ²	225–300
Shear Strength @ Yield	ASTM D732	psi	6,000
@ Ultimate			10,000
Shear Modulus	ASTM D732	psi	114,000
Deformation Under Load @ 4,000 psi @ 73°F	ASTM D621	%	0.2
@ 158°F			0.3
Thermal			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75 x 10 ⁻⁵
Coefficient of Thermal Conductivity	ASTM C177	Btu • in/hr • ft ² • °F	1.35
Specific Heat @ 40°C		cal/gm/°C	0.30
Heat Deflection Temperature @ 264 psi	ASTM D648	°F	270
@ 66 psi			280
Brittle Temperature	ASTM D746	°F	-211
Relative Thermal Index, Electrical properties	UL746B	°C	130
Relative Thermal Index, Mechanical properties with impact	UL746B	°C	125
Relative Thermal Index, Mechanical properties without impact	UL746B	°C	125
Flammability			
Horizontal Burn (Flame Spread) AEB	ASTM D635	in	<1

Property	Test Method	Units	Value
Electrical			
Dielectric Constant @ 10 Hz	ASTM D150	—	2.96
@ 60 Hz			3.17
Volume Resistivity	ASTM D257	ohm-cm	8.2 x 10 ¹⁶
Power Factor @ 60 Hz	ASTM D150		0.0009
@ 1,000,000 Hz			0.010
Arc Resistance	ASTM D495	sec	
Stainless Steel Strip Electrodes			10–11
Tungsten Electrodes			120

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative Plastics representative or SABIC Innovative Plastics Quality Services Department.

™ Trademarks of SABIC.

CODE COMPLIANCE

Underwriters Laboratories

LEXAN 903x Sheet is listed as a Burglary-Resisting Glazing Material according to UL Standard 972.

UL File Number: E121562

CONTACT US:

Middle East and Africa

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Email

sfs.info@sabic-ip.com

Americas

Specialty Film & Sheet
One Plastics Avenue
Pittsfield, MA 01201
USA
Toll-free 1 800 323 3783 ext.3
T 1 413 448 7125
F (888) 443 2033
E sfs.customerservice@sabic-ip.com

Europe

Specialty Film & Sheet
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E sfs.info@sabic-ip.com

Asia Pacific

Specialty Film & Sheet
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

* Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs

